



# FISi/ SI9270 Encapsulant

## FEATURES & BENEFITS

- 100% Solids / Solvent free
- Exceptionally fast cure
- Convenient 1:1 mix ratio
- No corrosive by-products
- Environmentally friendly
- Low shrinkage
- Virtually no exotherm
- No post-cure required
- Toughened for improved mechanical strength

## APPLICATIONS

- Automotive ECUs
- Outdoor junction boxes
- Semiconductor modules
- “Clam-shell” enclosures
- Cable splicing units
- Electronic potting

## AVAILABILITY

- 55-Gallon Drums
- 5-Gallon Pails
- 600 ml Side-by-side cartridges

## STORAGE / SHELF LIFE

SI9270 may be stored in original, unopened containers at, or below, 75F for up to one (1) year.

## DESCRIPTION

FISi/ SI9270 is a black, two-component, silicone-based potting and encapsulating compound with good flowability, long work-life, flexible cure schedule and flame resistance.

## TYPICAL PROPERTIES

Physical Property	Test Method	Performance Range
Appearance (mixed)	Visual	Charcoal liquid
Mix Ratio		1:1 By Volume (1:1 By Weight)
Viscosity (Mixed)	Brookfield	2000-3000 cps
Specific Gravity		1.35
Worklife @ 25C		15 -30 minutes
Cure Time @ 25C		3-4 hours
Shore Hardness	ASTM D 2240	50 Shore A
Service Temperature		-40C to 205C (-40F to 400F)
Fire Resistance	UI 94 – V0	Pending
Thermal Conductivity	ASTM E 1530	0.35 W/m-K
Dielectric Constant	ASTM D150	3.03 @100 Hz 2.98 @ 100 kHz
Dissipation Factor	ASTM D 150	0.015 @100Hz 0.0075 @100 kHz
Dielectric Strength	ASTM D149	350 V/mil

## ADDITIONAL INFORMATION

- Refer to Technical Bulletins for additional mixing, curing and handling procedures.
- As with any platinum-catalyzed silicone gel, the cure may be inhibited. Always check compatibility. Refer to Technical Bulletin for information.  
Not recommended for surfaces that are to be painted.

To the best of our knowledge, the information provide herein is accurate. However, Star Technology, Inc. does not assume any liability for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchaser in selecting the appropriate products for purchaser’s own testing. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein and in the Safety Data Sheet, we cannot guarantee that these are the only hazards that exist.